


WHAT IS CLAIMED IS:

1. A process of dyeing a molded article comprising the steps of
- (i) immersing at least a portion of said article in a dyeing bath that contains a carrier and a tinctorial amount of at least one dye, said bath maintained at a temperature of 90 to 99°C and
- (ii) retaining said portion in said bath for a period of time sufficient to allow a predetermined amount of dye to diffuse into said article, and

- (iii) removing said article from said bath,
- wherein molded article comprise at least one polymeric resin selected from the group consisting of (co)polyester, (co)polycarbonates, acrylonitrile-butadiene-styrene, polyamide, polyurethane, polyalkyl(meth)acrylate and styrene copolymers, and wherein said carrier conforms to




wherein R^2 and R^1 independently denote H or C₁₋₁₈ alkyl, benzyl, benzoyl or phenyl radical, n is 2 or 3 and m is 2-35.

2. The process of Claim 1 wherein the bath further contains a surfactant.

3. A process of dyeing a molded article comprising the steps of
- (i) immersing at least a portion of said article in a dyeing bath that contains a carrier and a tinctorial amount of at least one disperse dye, said bath maintained at a temperature of 90 to 99°C, and
- (ii) retaining said portion in said bath for a period of time sufficient to allow a predetermined amount of dye to diffuse into said article, and
- (iii) removing said article from said bath,

wherein molded article comprise at least one polymeric resin selected from the group consisting of (co)polyester, (co)polycarbonates, acrylonitrile-butadiene-styrene, polyamide, polyurethane, polyalkyl(meth)acrylate and styrene copolymers, and wherein said carrier conforms to

5



wherein R^2 and R^1 independently denote H or C_{1-18} alkyl, benzyl, benzoyl or phenyl radical, n is 2 or 3 and m is 2-35.

10

4. The process of Claim 3 wherein the bath further contains a surfactant.

15

5. The process of Claim 1 wherein R^2 denotes butyl and R^1 denote H.

6. The process of Claim 3 wherein R^2 denotes butyl and R^1 denote H.

20

7. The process of Claim 1 wherein dye is a water-insoluble dye selected from the group consisting of azo, diphenylamine and anthraquinone compounds.

25

8. The process of Claim 1 wherein R^2 and R^1 independently one of the other denotes benzyl, benzoyl or phenyl radical that are substituted in their aromatic rings by alkyl and/or halogen.


30

9. The process of Claim 3 wherein R^2 and R^1 independently one of the other denotes benzyl, benzoyl or phenyl radical that are substituted in their aromatic rings by alkyl and/or halogen.

10040338-110701

sub a'

10. A composition of matter containing a resinous component, a dye, a carrier and an optional surfactant wherein carrier conforms structurally to




5

wherein R^2 and R^1 independently denote H or C_{1-18} alkyl, benzyl, benzoyl or phenyl radical, n is 2 or 3 and m is 2-35, and wherein resinous component contains at least one member selected from the group consisting of (co)polyester, (co)polycarbonates, acrylonitrile-butadiene-styrene, polyamide, polyurethane, polyalkyl(meth)acrylate and styrene copolymers,

10

11. A composition of matter containing a resinous component, a disperse dye, a carrier and an optional surfactant wherein carrier conforms structurally to

15



20

wherein R^2 and R^1 independently denote H or C_{1-18} alkyl, benzyl, benzoyl or phenyl radical, n is 2 or 3 and m is 2-35, and wherein resinous component contains at least one member selected from the group consisting of (co)polyester, (co)polycarbonates, acrylonitrile-butadiene-styrene, polyamide, polyurethane, polyalkyl(meth)acrylate and styrene copolymers,

25

12. The process of Claim 1 wherein the molded article further comprise metal flakes.

30

13. The process of Claim 3 wherein the molded article further comprise metal flakes.

14. The process of Claim 1 wherein the molded article further comprise titanium dioxide.

15. The process of Claim 3 wherein the molded article further comprise titanium dioxide.

5 16. The process of Claim 1 wherein the molded article further comprise crosslinked polymethylmethacrylate minispheres.

10 17. The process of Claim 3 wherein the molded article further comprise crosslinked polymethylmethacrylate minispheres.

18. The process of Claim 1 wherein the resin is aromatic polycarbonate.

15 19. The process of Claim 1 wherein the resin is allyldiglycol carbonate.

20. A dip-dyed article prepared by the process of Claim 1.

21. A dip-dyed article prepared by the process of Claim 3.

Pub
a'
10/10/78 110701